

POLY S2 GREASE

BARDAHL POLY S2 GREASE is a new generation poly-synthetic grease formulated with a fully synthetic gelling agent, synthetic and paraffinic base oils.

POLY S2 is a long-lasting grease, resisting high temperatures and heavy loads.

I. PROPERTIES

Thanks to its synthetic components, BARDAHL POLY S2 grease has an outstanding efficiency for:

- ✓ Resistance to wear resulting from oxidation (the ASTM D 3336 Test shows that it lasts 5 times longer than a lithium-based grease).
- ✓ Resistance to extreme working conditions (400 kg at 4 ball test).
- ✓ Resistance to extreme loads, shocks , vibrations, ...
- ✓ Can be used from 30° C to + 170° C. Resists to peaks of + 200° C.
- \checkmark Resistance to water leashing and aggressive chemical products.
- ✓ Resistance to very rapid rotations: 12 000 rpm.
- ✓ Makes cold start easier thanks to a fluid base oil.
- ✓ Can be perfectly blended with other types of standard soap.
- ✓ Compatible with synthetic and natural water tightness gaskets.

NLGI GRADE	2		
PENETRATION		The penetration test measures the consistence of a greace	
60 HITS	265/295	The penetration test measures the consistence of a grease.	
AT 30°C	107		
GELLING AGENT	Synthetic poly-urea	New generation of synthetic gelling agent offering a very	
		high resistance to:	
		-heat	
		-water and chemical products	
		-heavy loads, shocks and vibrations	
VISCOSITY OF BASE OIL			
AT 40°C	100 mm²/s	The viscosity of oil is measured with a viscometer.	
AT 100°C	12,3 mm²/s		
DROP POINT	≥ +220°C	Poly S2 grease can be used from -30°C to +170°C.	
Ndm FACTOR	500 000	Poly S2 grease is suitable for very rapid rotations.	
AGING ASTM (D3336)	≥ 2500 hours at 100°C	Poly S2 is a long-lasting grease:	
	and 10000 rpm.	-A standard lithium complex grease lasts max. 500 hours	

III. TECHNICAL DATA



TECHNICAL DATA SHEET

			-A high temperature bentone grease lasts max. 1000 hours.
4 BALL TEST	r 🛛		Poly S2 is strengthened with antiseize and antiwear
Welding		> 400 kg	protection
Print		≤0,5 (40kg/1H)	
ASTM	D1264	≤2,75%	80°C water is sprayed in a bearing for one hour.
LEASHING TEST			
ANTI RUST Emcor test 0 (excel		0 (excellent)	Best score (no corrosion)

II. AVAILABILITY

BARDAHL POLY S2 GREASE is available in:

400gr cartridge	Case of 12 cartridges	Reference 1700
200gr tube	Case of 12 tubes	Reference 1701
1kg pail	Case of 12 pails	Reference 1702
4,5 kg pail	Case of 4 pails	Reference 1703
16 kg bucket	UNIT	Reference 1704
50 kg drum	UNIT	Reference 1705
185 kg drum	UNIT	Reference 1706